



| CHEMICAL RESISTANCE OF THE U FILL MATERIAL

	Nylon	Polypropylene	Polyethylene	Polyester	Natural fiber	Fill material
Acetaldehyde 100	U	20				
Acetic acid	U	20	20	20	20	
Alcohol (benzil)	U					
Alcohol (methyl, ethyl) 100%.		U				
Alum						
Aluminium sulphate					U	
Liquid ammonia		U	U	U		
Ammonium bicarbonate						
Ammonium fluoride				20	U	
Ammonium persulfate	U				U	U
Ammonium sulphate						
Ammonium sulphide				U		
Amyl acetate	U	U	U			
Anti-freeze			20			
Barium sulfide	U				U	
Bleaching powder (diluted)	U	U	U	U	U	
Brine						
Calcium chloride						
Carbon tetrachloride		U	U			
Chlorine, water	U	U				
Cresol	U		U	20		
Copper		U				

	Nylon	Polypropylene	Polyethylene	Polyester	Natural fiber	Fill material
Detergents (aqueous)						
Photo developing chemicals				U	U	U
Ether		U	U			
Ethyl acetate		U	U			
Ferric chloride			20	20		U
Hexafluorosilicic acid 32%	U		20		U	U
Formaldehyde 40%	U					
Formic acid 50%	U					U
Hydrobromic acid 50%	U				U	U
Hydrochloric acid 50%	U	20			U	U
Hydrofluoric acid 40%	U	20			U	U
Hydrogen peroxide 30%	U	20	20			
Hydroquinone (non-aqueous)						
Tetraethyl lead			20			
Mercuric Chloride	U			20		
Dichloromethane	U	U	U	U		
Methyl ethyl ketone	U	U				
Petroleum oils		20	U			
Naphta						
Naphthalene				20		
Nitric acid 10%					U	U
Oxalic acid 10	20					U

	Nylon	Polypropylene	Polyethylene	Polyester	Natural fiber	Fill material
Phosphoric acid 20%	20					U
Polyester resin		20				
Potassium bicarbonate						
Silicone oil						
Sodium bisulphite					U	U
Sodium bisulphite					U	U
Sodium carbonate					U	20
Caustic soda					U	U
Sodium nitrate						
Sodium sulfide					U	U
Stannic chloride					20	U
Starch						
Stearic acid				20		
Sugar						
Sulphur				20		
Sulphuric acid	20					
Tallow				20	U	
Tetrahydrofuran			U	U		
Toluene			U	U		
Tricresyl phosphate					U	
Tri-ethanolamine						
White Spirit						
Yeast	U					
Zinc chloride	U					20